

Deutsch

Brillant-Etiketten

Ausführung: Brillant Standard (B) / Brillant gestanzt (BG) / Brillant selbstklebend (BS)

WICHTIG! Zu Ihrer eigenen Sicherheit bitten wir vor Einsatz der gelieferten Embleme diese auf Richtigkeit der Farben, Rechtschreibung, Größe usw. zu überprüfen. **Wir erstatten keine bedruckten Textilien!** Prüfen Sie bitte unbedingt vorher, ob die verwendeten Textilien für diese Emblemeart geeignet sind! Generell sind Vorversuche vor jeder Anwendung notwendig.

Ausführung:	Brillant Standard (B) / Brillant gestanzt (BG) / Brillant selbstklebend (BS)									
Waschprogramm	Patchtemperatur						Zeit [sec]			Druck
	Ausführung	Baumwolle	Baumwoll-Mischgewebe	Polyester	Nylon	Softshell	Vor-patchen	Patchen	Nach-patchen	Bar
75 °C - 85 °C Industriewäsche	Brillant Standard (B)	204 °C	204 °C	204 °C	/	/	/	10-12	/	4-6
75 °C - 85 °C Industriewäsche	Brillant gestanzt (BG)	204 °C	204 °C	204 °C	/	/	/	10-12	/	4-6
75 °C - 85 °C Industriewäsche	Brillant selbstklebend (BS)	204 °C	204 °C	204 °C	/	/	/	12-15	/	4-6

- Es handelt sich um empfohlene Standardparameter. Bei speziellen / industriellen Anwendungen können die Parameter angepasst werden (**Tests nötig**)

Patchvorgang: Emblem mit der Vorderseite nach oben auf dem Stoff platzieren. Überdrucken von Nähten vermeiden / patchen

Allgemeines:

- Das Überbügeln ist mit **max. Stufe 3** des Bügeleisens möglich, bitte achten Sie jedoch darauf, zügig über das Emblem zu bügeln. Das Bügeleisen muss sauber und frei von Rückständen und Ablagerungen sein.
- Die Embleme **dürfen gemangelt werden**.
- Embleme sind zur Bearbeitung mit dem **Finisher** geeignet.
- Die Räumlichkeit sollte ausreichend belüftet werden.
- Mögliche Lagerzeit: 2 Jahre bei sachgemäßer Lagerung (dunkel, trocken, Zimmertemperatur, verschlossene Verpackung)

English

Brillant emblems

Version: Brillant standard (B) / Brillant die-cut (BG) / Brillant self-adhesive (BS)

IMPORTANT! For your own safety, please check that the supplied emblems are correct in terms of colours, spelling, size etc., before they are used. **We do not replace any printed textiles!** Please always test your textiles in advance to make sure that they are suitable for this kind of emblems. Pretests are generally needed before each use.

Version:	Brillant standard (B) / Brillant die-cut (BG) / Brillant self-adhesive (BS)									
Washing program	Heat-seal temperature						Time [sec]			Pressure
	Version	Cotton	Cotton blend fabrics	Polyester	Nylon	Softshell	Pre-heat-sealing	Heat-sealing	Repeat heat-sealing	Bar
75 °C - 85 °C Industrial washing	Brillant standard (B)	204 °C	204 °C	204 °C	/	/	/	10-12	/	4-6
75 °C - 85 °C Industrial washing	Brillant die-cut (BG)	204 °C	204 °C	204 °C	/	/	/	10-12	/	4-6
75 °C - 85 °C Industrial washing	Brillant self-adhesive (BS)	204 °C	204 °C	204 °C	/	/	/	12-15	/	4-6

- These are recommended parameters. It is generally possible to adjust those parameters for special industrial applications, but only with appropriate testing.

Heat-sealing: Place the emblem on the fabric with the front upwards. Avoid printing over seams / Heat-sealing

General Information:

- Can be ironed **up to level 3** max. Please iron quickly over the emblem. The iron has to be clean and free of residues.
- Emblems **can be mangled**.
- Emblems are **suitable for processing with the finisher**.
- The room should be adequately ventilated.
- Storage period: 2 years under appropriate storage conditions (dark, dry, closed packaging, at room temperature)

Datel	Dokumentenart	Kurzbezeichnung	Seite
VH001_V(7).doc	Kundenunterlagen	VH 001	1 / 2

ThermoTex Europe AG, 6340 Baar, SCHWEIZ, Tel. +41 61 751 91 00, info@thermo-tex.ch, www.thermo-tex.ch

ThermoTex Nagel GmbH, 77746 Schutterwald, DEUTSCHLAND, Tel. +49 781 9616-0, info@thermo-tex.de, www.thermo-tex.de